FICHA TÉCNICA PROVISIONAL - FICHE TECHNIQUE PROVISOIRE
PROVISIONAL TECHNICAL CARD - PROVISORISCHE TECHNISCHE KARTE

Tejido + 838 Acabado PURSAN BP ing 90 gr

Composición Composition Stoffzusammentsetzung	Tejido – 75 gr./m² Recubrimiento 100 % PU - 90 gr./m²
Peso/m² Poids/m² Weight/m² Gewicht/m²	165 gr. (+/- 5%)
Ancho Largeur Width Breite	220 cm
Impermeabilidad (Columna de agua) Imperméabilité (Colonne d'eau) Impermeability (Water Column) Wasserfestigkeit (Wassersäule)	>200 cm
Esterilización en autoclave Stérilisation en autoclave Autoclave Sterilization Autoklavsterilisierung	Resistente a la esterilización a 120ºC Résistant à la stérilisation à 120ºC Resistant to sterilization at 120ºC Sterilisierbar bei 120ºC
Transpiración Transpiration Breathability Atmungaktiv	> 1.000 gr/m²/24 Horas/Heures/Hours/Stunden
Características ignífugas Caractéristiques ignifuges Fireproof Properties Feuerfestigkeit	Carga SIG en capa de PU A verificar articulo final
Antibacterias – Fungicida Antibactérien – Fongicide Antibacterial – Fungicide Bakterizid - Fungizidveredlung	Norm:ISO 846:1997
Encogimiento al lavado a 95ºC (1 ciclo) Retrait au lavage à 95ºC (premier lavage) Shrinkage at 95ºC (After first washing) Scrumpfung nach washen bei 95ºC (Einmal waschen)	Urdimbre/Chaîne/Warp/Kette: < pendiente % Trama/Trame/Weft/Schuss : < pendiente %

Normas de mantenimiento / Normes d'entretien / Washing and Ironing instructions / Pflegehinweise

PHTHALATE FREE

To bear in mind:
This article has been conceived and formulated to be used with the fabric on the outside (upperside) and PU as underside. In case it's being used on the oposite side, PU in the upperside, the possible stains musn't be neither cleaned nor disinfected by rubbing the PU surface instead of washing the whole mattress protector. Then this kind of operations can damage the polyurethane layers, occasionating the deterioration of its properties, it doesn't matter the disinfection product used.